



Härter 2

Klebstoffsorte	Polyisocyanat - Lösung
Typische Anwendungsbereiche	Zur Vernetzung von Lösemittelklebstoffen auf Basis von PUR
Hinweise	sehr langsam reagierend

Typische Eigenschaften

Eigenschaften	Wert
Dichte (20°C)	ca. 1,17 g/cm ³
Festkörper	ca. 75 %
pH- Wert	
Farbe	gelblich, klar
Kälteverhalten	nicht frostempfindlich
Lagerbeständigkeit	12 Monate

Anwendungshinweise	Bei der Verarbeitung der Klebstoff / Härtermischung unbedingt auf die im jeweiligen TDS des verwendeten Klebstoffes aufgeführte Topfzeit sowie Verarbeitungsspanne achten.
Bemerkungen	Hierzu unbedingt die Angaben im jeweiligen TDS des verwendeten Klebstoffes beachten. Zugabemenge zum Klebstoff in der Regel 5 Gew. %, in Ausnahmefällen bis 10 Gew. %.
Verarbeitungstemperatur	Raumtemperatur, nicht unter + 16 °C
Reinigungshinweise	Isa - Verdünner 1
Typische Verpackung	Bitte wenden Sie sich bezüglich der verfügbaren Verpackungsoptionen an Ihr lokales Vertriebsbüro.



Lagerbedingungen	bei trockener Lagerung zwischen + 5°C bis + 25°C in verschlossenen Gebinden. Angebrochene Gebinde luftdicht verschließen, vor Feuchtigkeitseinwirkung schützen und möglichst schnell verbrauchen.
Hinweise zur Entsorgung	Hinweise zur Entsorgung entnehmen Sie bitte dem Materialsicherheitsdatenblatt.
Sicherheitshinweise	Sicherheitshinweise entnehmen Sie bitte dem Materialsicherheitsdatenblatt.

Our Focus is Clear. Perfecting Adhesives.

IMPORTANT: The information, specifications, procedures and recommendations herein (together "information") are based on our experience and we believe these to be accurate. No representation, guarantee or warranty is made as to the accuracy or completeness of the information or that the information will avoid losses or damages or give desired results. It is purchaser's sole responsibility to test and determine the suitability of any product for the intended use. Tests should be repeated if materials or conditions change in any way. No employee, distributor or agent has any right to change these facts and offer a guarantee of performance.

NOTE TO USER: *by ordering/receiving product you accept the H.B. Fuller General Terms and Conditions of Sale applicable in the region. Please request a copy if you have not received these.* These Terms and Conditions contain disclaimers of implied warranties (including but not limited to disclaiming warranties of fitness for a particular purpose) and limits of liability. *All other terms are rejected.* In any event, **the total aggregate liability of H.B. Fuller for any claim or series of related claims however arising, in contract, tort (including negligence), breach of statutory duty, misrepresentation, strict liability or otherwise, is limited to replacement of affected products or refund of the purchase price for affected products.** H.B. Fuller shall not be liable for **loss of profit, loss of margin, loss of contract, loss of business, loss of goodwill or any indirect or consequential losses** arising out of or in connection with product supply.

Nothing in any term shall operate to exclude or limit H.B. Fuller's liability for fraud, gross negligence or for death or personal injury caused by negligence or for breach of any mandatory implied terms.

Austria
07242 409 341
Germany
04131 705 275
Switzerland
0049 4131 705 275
UK
00800 3855 3711

France
0800 917 537
Italy
800 985 778
Spain
800 099 493
Portugal
22 928 82 00

Belgium
0800 49 740
Netherlands
0800 020 3433
Luxemburg
00800 3855 3711
Sweden
031 496 640

Poland
00800 1213 827
Eastern Europe
0043 7242 409 365
Russia
0043 7242 409 346
India
0091 22 61450500

Egypt
0020 238 333 731
Turkey
0090 216 455 97 30

H.B. Fuller Europe
info-europe@hbfuller.com

